

EU.P.S. MASTER P



General description: coloured asphalt shingle



bituminous compound	-		APP modified bitumen	
length	EN 544	mm	1000	+/-3
width	EN 544	mm	337	+/-3
thickness	-	mm	3,1/6,2	+/-10%
exposed area	-	mm	143	-
maximum tolerance between the two pieces in lamination, both directions				+/-3 mm
axis of nailing lane (from exposed area)	-	mm	14	+/-3

Physical-chemical properties

weight	-	kg/m ²	10,8	+/-8%
mass of the fibreglass mat	-	g/m ²	100	+/-10%
granules single layer	EN 544	g/m ²	>1400	-
mechanical resistance MD/CMD	EN 544	N/5 cm	>750/>450	-
nail resistance	EN 544	N	>100	-
granules adhesion	EN 544	-g	1,5	+/-0,15

Fire behaviour

classification according	EN 13501-5	B roof (t1)
classification according	EN 13501-1	E

Wrapping

type	cartboard
shingles for bundle	18
m ² /bundle	2,57
m ² /pallet	123,36



The technical data sheet may be updated by the manufacturer